



Chevaline Epistixx CP Floor Coating

Epoxy floor coating system for interior carparks applied to concrete surfaces

Specification No: P1641

Date Prepared: May 2023

Project & Address:

Certified Applicator:

Building Contractor:

Building Owner/Property Manager:

1. Statement of Intent

- (a) This checklist is to be completed by both the Equus Applicator and the Building Contractor, as a step by step record of compliance with both the Equus Specification provided for the contract, and the requirements of the Manufacturers for Warranty.
- (b) A copy of this checklist must be forwarded to the nearest Regional Office of Equus Industries Ltd. A Warranty will not be issued by Equus Industries Ltd. without a copy of this Checklist being filed.
- (a) A copy of this checklist should form part of the Contract Documentation filed with the Property Manager on job completion.

2. Areas Treated

The areas to which the coating applied are detailed below, with reference to plans (where appropriate).

3. Sign Off

We confirm that all applicable processes listed in Section 4 have been correctly completed and that sign-off on each stage has been made by a person with the authority to do so.

For: _____ (Signature)
(Building Contractor)

Date: ____ / ____ / ____ (Name)

For: _____ (Signature)
(Equus Applicator)

Date: ____ / ____ / ____ (Name)



4. Checklist And Method Statement

* Denotes those processes which must be signed off by the Building Contractor as well.

No.	Process	Min. WFT	Completed On	Building Contractor	Equus Contractor	Notes
1.*	Concrete must be dry, firm, clean, and free of laitance, dust, grease, oil and other contaminants.					
2.*	Surface defects to be filled with ASO-CRET BIS product range or other approved mix. Any major concrete dishing or ponding is to be discussed with Equus to work out a remedy.					
4.	Concrete surface satisfactory for installation of coating by Equus Certified Applicator.					
5	All surfaces are primed with Chevaline Epistixx primer, mixed and diluted up to 40%, at a spread rate of 8-10m ² per litre. Allow to dry overnight.	60				
	Hairline cracks up to 1mm to be filled with a Chevaline Epistixx mortar. Cracks up to 3mm to be coated with a strip of Matacryn Thix and jointing tape.					
6.	Bodycoat: Primed surfaces receive one coat of Chevaline Epistixx CP , mixed and diluted up to 10%, at 6-7m ² per litre. Allow to dry for a minimum of 6-8 hours.	125				
7.	Topcoat: All surfaces to receive one coat of Chevaline Epistixx CP , mixed and diluted up to 10%, at 6-7m ² per litre. Allow to cure at least 7 days before allowing other than foot traffic on the surface .	125				
	Expansion joints shall filled with an oversized backing rod, and sealed with Dy-monic 100 sealant. This shall be expressed through the system.					
8.	Where required, service lane markings shall be applied using Chevaline Epistixx CP in the appropriate colour. Spreading rate will be 6-8 sqm/litre and markings shall be neatly masked to give a 'crisp' edge.					
9.*	System to be inspected upon completion.					