



291
1 pages

PRODUCT
DATA
SHEET

Keim Lotexan

Product Description:

Water repellent impregnation to reduce the water absorption of porous building materials.

Composition:

Low-molecular siloxane in hydrocarbon mixture. Siloxane concentration 8%.

Colour:

Colourless

Material Data:

Density: approx. 0.8 g/cm³
Flashpoint: -3°C
Miscibility: -

Packaging:

5 and 25 litre containers

Storage:

Approx. 12 months, if kept cool but frost free in tightly closed containers. Store dry, do not expose to direct heat. After use, cans should be closed properly to prevent penetration of moisture.

Identification according to working material instructions:

Inflammable, do not smoke when processing.
Take precaution that it will not get into the canalisation.

Field of Application:

To get subsequent impermeability to water for Keim coatings. Colourless impregnation of all mineral surfaces such as natural stone, masonry, brick and render etc. also after strengthening with Keim Silex OH.

Consumption:

0.2-1 l/m² depending on the absorbency.

Tools:

Flow coating process by means of spray equipment or with brush wet-in-wet.

Temperature:

Do not process below 5°C of recirculated air and surface.

Equus Industries Ltd
PO Box 601
Blenheim
Phone: 03 578 0214 Fax 03 578 0919
Email: admin@equus.co.nz
Web: www.equus.co.nz