

COLPHENE BSW V



Description:

COLPHENE BSW V is a high-performance waterproofing membrane composed of SBS modified bitumen and a composite reinforcement.

The topside is covered with specially engineered carbon dioxide crystals and the underside is covered by a silicon release film. **COLPHENE BSW V** is designed for vertical blind side waterproofing applications.

Field of Application:

COLPHENE BSW V is a pre-applied membrane designed for vertical blind side waterproofing applications (below grade and tanking works).

COLPHENE BSW V can be used for the following general applications:

- Retaining walls
- Foundations

Application Method:

COLPHENE BSW V is a self-adhered 'peel and stick' membrane installed over a prepared substrate using Equus Peel & Stick Primer and neoprene roller.

DUO SELVEDGE

Over the entire width of DUO SELVEDGE, 60% of the surface is covered with exposed sticky bitumen. The remaining surface of the selvedge (40%) is covered by a thermofusible plastic film to seal overlap by heat-welding with a propane torch or with the SOPRAMATIC automatic hot-air welder.

Installation Procedure:

SUBSTRATE

- No work should be started until all surfaces are smooth, dry and free of ice, snow or any other substance that may prevent the membrane from adhering properly.
- Commencement of installation shall be taken as acceptance of the substrate by the Applicator.
- The use of Equus Peel & Stick Primer is required before installation of COLPHENE BSW V membrane if the adhesion is not enough.

INSTALLATION

- COLPHENE BSW V is installed in vertical strips of 5 m maximum onto acceptable substrate.
- COLPHENE BSW V membrane is adhered to substrate by peeling off the silicone release film.
- Side lap joints must be a minimum of 100 mm and end lap joints must be a minimum of 150 mm.
- Once installed, pressure must be applied over the whole surface using a membrane roller to ensure good contact.
- Membrane overlaps are sealed, by heat welding, with a propane torch or using an electric hot-air welder.
- The uppermost edge of each strip must be mechanically fastened to substrate using round plates of 50 mm diameter and appropriate fasteners for base material every 300 mm on center.

For complete installation specification and information please contact your local Equus Representative.

Packaging:

Roll dimensions: 1 m x 10 m
Roll weight: 35 kg
Rolls per pallet: 30

Storage & Handling:

Rolls must be stored upright, with the selvedge side on top. If the products are stored outdoors, cover them with an opaque protection cover after removal of the delivery packaging.

Properties:

Property	Standards	COLPHENE BSW V
Tensile strength at peak load, MD/XD	ASTM D5147	15.3 / 11.5 kN/m
Elongation at break, MD/XD	ASTM D5147	60 / 56 %
Tear strength, MD/XD	ASTM D5147	575 N / 500 N
Low temperature flexibility	ASTM D5147	Unaffected at -20 °C
Puncture resistance	ASTM E154	1100 N
Water vapour permeance	ASTM E96 (Method B)	<2.1 ng / Pa•s•m ²
Water absorption	ASTM D570 @ 24 hours	<0.5 %
Adhesion to poured concrete, 22 °C	ASTM D903 modified (Peeled at 50 mm/min)	4200 N/m
Resistance to hydrostatic head	ASTM D5385	> 110 m
Lateral water migration	ASTM D5385 modified	> 110 m
Gas permeability (methane) - (cm ² / s @ 1 atm) - (cm ³ x cm / cm ² x s s Pa)	ASTM D1434	4.12 x 10 ⁻⁷ 4.06 x 10 ⁻¹²
Volume resistivity (ohms-cm)	ASTM D257	1.57 x 10 ¹⁴
UV exposure	-	Up to 60 days

Statement of Responsibility:

The technical information and application advice given in this publication is based on the present state of our best knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by Commonwealth or State Legislation. The owner, their representative and/or the contractor are responsible for checking the suitability of products for their intended use.

Equus Industries Ltd
PO Box 601
Blenheim
Phone: 03 578 0214 Fax 03 578 0919
Email: admin@equus.nz
Website: www.equus.nz
January 2024