

# Thermexx FC Binder

## For Thermexx Fairing Compound

### Purpose & Areas Of Use:

A cementitious fairing compound is produced from **Thermexx FC Binder** combined grey Portland or white cement.

### Product:

A modified, acrylic polymer reinforced liquid component containing lightweight fillers for ease of application and finishing.

Supplied on as the **Thermexx FC Binder** component to be mixed with locally sourced cement.

### Process Compatibility:

Can be used as a leveling or repair compound under most Equus wall coating systems.

### Standard Pack:

15 litre plastic pails.

### Physical Properties:

Appearance	Grey Viscous Liquid
Specific Gravity	0.8 - 0.9
Flash Point	Not Applicable– Waterbased
pH	9 - 10

### Surface Preparation:

Ensure that the cementitious surface to be treated is sound and free from any laitance, dust, dirt, grease, oil or release agents.

On porous surfaces, reduce suction by dampening the surface with clean water.

### Application:

Use a steel trowel to lightly skim the mixed compound on to the surface up to a thickness of approximately 3 mm.

### Cure Time:

Allow for a minimum of 24 hours for the compound to cure. (Standard Conditions of 23°C ± 60% R.H)

### Finishing:

Sand smooth with a fine grit abrasive paper and apply finishing coats, as required.

### Clean Up:

Clean tools with clean water immediately after use.

### Health & Safety:

**Thermexx FC Binder** is a non flammable filled emulsion, is non-toxic and safe to handle. The normal precautions for skin care taken when handling cement based materials must be observed as this compound is being, or has been mixed.

Equus Industries Ltd  
PO Box 601  
Blenheim  
Phone: 03 578 0214 Fax  
Email: [admin@equus.nz](mailto:admin@equus.nz)  
Web: [www.equus.nz](http://www.equus.nz)