

ASOCRET-KS/HB

Mineral based corrosion protection and bonding coat

Properties:

- Resistant to saponification
- Resistant to frost and de-icing salts
- Very easy to use even on vertical and "overhead" areas

Areas of application:


ASOCRET-KS/HB is used for protecting steel reinforcement against corrosion during concrete restoration work and also as a bonding coat onto concrete and mortar substrates.

ASOCRET-KS/HB is a component of the concrete restoration system with the product ASOCRET-BIS-5/40.

Technical data:

Basis:	Factory blended mortar
Grain size:	up to 0.5 mm
Bulk density:	1.6 kg/dm ³
Material consumption:	approx. 1.6 kg/m ² /mm
Pot life:	approx. 60 minutes
Application/ substrate temp:	+5 °C to +30 °C
Tensile adhesion strength:	> 1.5 N/mm ²
Cleaning:	Clean tools with water immediately after use.
Packaging:	6 kg and 25 kg bag
Storage:	cool and dry, 12 months in the original unopened packaging. Use opened packaging promptly.

*)At +23°C and 50% relative humidity. The weather and site conditions may lengthen or shorten the given data.

	
SCHOMBURG GmbH & Co. KG Aquafinstraße 2-8 D-32760 Detmold 10 2 05550	
DIN EN 15047 ASOCRET-KS/HB Product for the corrosion protection of reinforcement DIN EN 15047: ZA. 1a	
Shear resistance	NPD
Corrosion protection	passed

NPD = „No Performance Determined“

Surface preparation:

Cement-based surfaces must be solid, have a good grip and be load-bearing, free from cement laitance, loose parts as well as adhesion reducing materials such as release agents, dust, laitance layers etc. Dependent on the project, substrate treatment is to be carried out, e.g. grip, shot or high pressure water blasting (500-2000 bar), scabbling or planing. The prepared substrate must possess an open pored surface structure.

Minimum age of the concrete substrate: 28 days
 Tensile adhesion strength of the concrete substrate: min. 1.5 N/mm²

The exposed reinforcing steel must be cleaned to standard purity grade SA 2.5 using suitable measures and be free from rust, dust and grease.

Adequately pre-wet the treated substrate 24 hours as well as hours before mortar application and the substrate must be matt damp at the time the mortar is applied.

Product preparation:

Water demand:
 - Bonding coat:
 approx. 6.75 - 7.00 l / 25 kg or 1.60 - 1.70 l / 6 kg
 - Corrosion protection:
 approx. 5.50 - 5.075 l / 25 kg or 1.30 - 1.40 l / 6 kg

Place clean water into a clean mixing bucket - dependent on the desired consistency - and mix with as much dry powder as is necessary to achieve a lump-free, smooth paste using a mechanical mixer (drill with paddle approx. 300-700 rpm). The mixing time is approx. 2-3 minutes. Allow to stand for 5 minutes then mix once again. Only mix as much material as can be used within max. 60 minutes.

Method of Application:

Corrosion protection: Evenly apply two coats of ASOCRET-KS/HB to the de-rusted steel reinforcement using a paint brush. The steel reinforcement may be damp. The second layer can be applied after waiting for at least 6 hours, as soon as the first layer is crush proof. After allowing the second coat to harden for approx. 6 hours, the repair mortar ASOCRET-BIS-5/40 can be applied.

Bonding Coat: ASOCRET-KS/HB is brushed in a single application to fully cover the area using a hard brush deep into the pores of the prepared substrate. The following layer of the repair mortar ASOCRET-BIS-5/40 must be applied whilst the bonding coat is still wet. Where work is interrupted or the material hardens, the bonding coat must be allowed to fully harden. Afterwards repeat the application inclusive of bonding coat once an appropriate time has elapsed.



Advice:

- Prior to implementing any concrete restoration measures the actual condition should generally be assessed by an authorized expert and/or a Structural Engineer. The inspection protocol is to be given to the contractor before the commencement of the restoration works.
- Protect areas not being treated from the effects of ASOCRET-KS/HB.
- Do not add additional water or powder to material that has begun to stiffen in an attempt to restore the original consistency. There is a risk of inadequate strength development.
- Applications that are not clearly explained in this technical data sheet may only be carried out after consultation with and written confirmation from your Equus Representative.

Please observe a current valid EU Health & Safety data sheet.

GISCODE: ZP1

**Equus Industries Ltd
PO Box 601
Blenheim
Phone: 03 578 0214
Email: admin@equus.nz
Web: www.equus.nz
December 2018**